


PART NUMBER	COLOR	SIZE (in)	SUPPLIED	AFTER RECOVERY	
			MIN. INSIDE DIAMETER (D) (in)	MIN. INSIDE DIAMETER (d) (in)	TOTAL WALL THICKNESS (t) (in)
980600	CLEAR	1/8"	0.125984252	0.039370079	0.039±0.00787
980610	CLEAR	3/16"	0.18503937	0.059055118	0.04331±0.00984
980620	CLEAR	1/4"	0.251968504	0.078740157	0.0472±0.00984
980630	CLEAR	3/8"	0.374015748	0.118110236	0.0531±0.00984
980640	CLEAR	1/2"	0.5	0.157480315	0.0689±0.0118
980650	CLEAR	3/4"	0.751968504	0.236220472	0.0787±0.0118
980660	CLEAR	1"	1	0.31496063	0.09055±0.0118
980670	CLEAR	1-1/2"	1.57480315	0.511811024	0.10039±0.0118



	HEAT SHRINK TUBING - 4 ft CLEAR
	AFTER AGING
SHRINK TEMPERATURE	≥90°C
TEMPERATURE RANGE	-40-105°C
LONGITUDINAL SHRINKING RATIO	10~10%
TENSILE STRENGTH	≥10.4 Mpa
ELONGATION RATIO	≥200%
DIELECTRIC VOLTAGE WITHSTAND	600V
VOLUME RESISTIVITY	≥1013Ω·CM
VOLTAGE RESISTANCE	≥2500 (60s)
FLAMMABILITY	NON FLAME RETARDANT
COPPER CORROSION	NONE
NOT TO SCALE	