


PART NUMBER	COLOR	SIZE (in)	SUPPLIED	AFTER RECOVERY	
			INSIDE DIAMETER (D) (in)	INSIDE DIAMETER (d) (in)	TOTAL WALL THICKNESS (t) (in)
98082505	BLACK	1/4"	0.251968504	0.059055118	0.05708±0.00984
98083005	BLACK	5/16"	0.31496063	0.078740157	0.06102±0.00984
98083505	BLACK	1/2"	0.472440945	0.118110236	0.0807±0.0118
98084505	BLACK	3/4"	0.708661417	0.177165354	0.09251±0.01377
98082500	RED	1/4"	0.251968504	0.059055118	0.05708±0.00984
98083000	RED	5/16"	0.31496063	0.078740157	0.06102±0.00984
98083500	RED	1/2"	0.472440945	0.118110236	0.0807±0.0118
98084500	RED	3/4"	0.708661417	0.177165354	0.09251±0.01377



	HEAT SHRINK TUBING - 4 ft 4:1 ADHESIVE LINED
	AFTER AGING
SHRINK TEMPERATURE	110°C
TEMPERATURE RANGE	-55-110°C
LONGITUDINAL CHANGE	0~10%
TENSILE STRENGTH	≥10.4 Mpa
ELONGATION RATIO	≥400%
TENSILE STRENGTH	≥12MPA
ELONGATION RATIO	≥300%
DIELECTRIC STRENGTH	≥20 kV/mm
VOLUME RESISTIVITY	≥1014Ω-cm
STABILITY OF COPPER	PASS
CONCENTRICITY	≥65%
STRESS CRACKING RESISTANCE	NO CRACKING
WATER ABSORPTION	<0.2%
SOFTEN POINT	85°C
PEEL STRENGTH	4N/cm
STABILITY OF COPPER	NO CORROSION
ANTIMICROBIAL PROPERTIES	PASS
NOT TO SCALE	