


PART NUMBER	COLOR	SIZE (in)	SUPPLIED		AFTER RECOVERY
			MIN. INSIDE DIAMETER (D) (in)	MIN. INSIDE DIAMETER (d) (in)	TOTAL WALL THICKNESS (t) (in)
91062005	BLACK	3/16"	0.125984252	0.039370079	0.039±0.00787
91062505	BLACK	1/4"	0.18503937	0.059055118	0.04331±0.00984
91063005	BLACK	3/8"	0.251968504	0.078740157	0.0472±0.00984
91063505	BLACK	1/2"	0.5	0.157480315	0.0689±0.0118



	HEAT SHRINK TUBING - 1-1/4" DUAL WALL
AFTER AGING	
SHRINK TEMPERATURE	≥110°C
SHRINK TIME	5 MINUTES
TEMPERATURE RANGE	-40-125°C
LONGITUDINAL SHRINKING RATIO	10~10%
TENSILE STRENGTH	≥10.4 Mpa
ELONGATION RATIO	≥200%
AGING IN CIRCULATING-AIR OVEN	(158±1.0)°C, 168 HOURS
TENSILE STRENGTH	≥7.3MPa
ELONGATION RATIO	≥100%
DIELECTRIC VOLTAGE WITHSTAND	600V
VOLUME RESISTIVITY	≥1014Ω·cm
VOLTAGE RESISTANCE	≥2500 (60s)
FLAMMABILITY	VW-1
NOT TO SCALE	