


PART NUMBER	COLOR	SIZE (IN)	SUPPLIED		AFTER RECOVERY	
			INSIDE DIAMETER (D)	WALL THICKNESS (T)	INSIDE DIAMETER (d)	WALL THICKNESS (t)
98030005	BLACK	1/16"	0.07874±0.005905	0.007874±0.002362	≤0.0314	0.01574±0.002362
98031505	BLACK	1/8"	0.13779±0.005905	0.009842±0.002362	≤0.04921	0.01811±0.003149
98030505	BLACK	3/16"	0.19685±0.007874	0.009842±0.002362	≤0.08858	0.02125±0.003149
98032505	BLACK	1/4"	0.255906±0.007874	0.009842±0.002362	≤0.11811	0.01968±0.003149
98029505	BLACK	3/8"	0.381890±0.011811	0.014173±0.003543	≤0.17716	0.02834±0.003937
98033505	BLACK	1/2"	0.5±0.011811	0.01417±0.003543	≤0.23622	0.02834±0.003937
98034505	BLACK	3/4"	0.73622±0.019685	0.01575±.003937	≤0.35433	0.03071±0.003937
98035505	BLACK	1"	1.02362±0.019685	0.01811±0.004724	≤0.49213	0.03543±0.00591
98036505	BLACK	1-1/2"	1.61417±0.031496	0.019685±0.005118	≤0.82677	0.045275±0.00591
98030001	RED	1/16"	0.07874±0.005905	0.007874±0.002362	≤0.0314	0.01574±0.002362
98031501	RED	1/8"	0.13779±0.005905	0.009842±0.002362	≤0.04921	0.01811±0.003149
98030501	RED	3/16"	0.19685±0.007874	0.009842±0.002362	≤0.08858	0.02125±0.003149
98032501	RED	1/4"	0.255906±0.007874	0.009842±0.002362	≤0.11811	0.01968±0.003149
98029501	RED	3/8"	0.381890±0.011811	0.014173±0.003543	≤0.17716	0.02834±0.003937
98033501	RED	1/2"	0.5±0.011811	0.01417±0.003543	≤0.23622	0.02834±0.003937
98034501	RED	3/4"	0.73622±0.019685	0.01575±.003937	≤0.35433	0.03071±0.003937
98035501	RED	1"	1.02362±0.019685	0.01811±0.004724	≤0.49213	0.03543±0.00591
98036501	RED	1-1/2"	1.61417±0.031496	0.019685±0.005118	≤0.82677	0.045275±0.00591
98030003	CLEAR	1/16"	0.07874±0.005905	0.007874±0.002362	≤0.0314	0.01574±0.002362
98031503	CLEAR	1/8"	0.13779±0.005905	0.009842±0.002362	≤0.04921	0.01811±0.003149
98030503	CLEAR	3/16"	0.19685±0.007874	0.009842±0.002362	≤0.08858	0.02125±0.003149
98032503	CLEAR	1/4"	0.255906±0.007874	0.009842±0.002362	≤0.11811	0.01968±0.003149
98029503	CLEAR	3/8"	0.381890±0.011811	0.014173±0.003543	≤0.17716	0.02834±0.003937
98033503	CLEAR	1/2"	0.5±0.011811	0.01417±0.003543	≤0.23622	0.02834±0.003937
98034503	CLEAR	3/4"	0.73622±0.019685	0.01575±.003937	≤0.35433	0.03071±0.003937
98035503	CLEAR	1"	1.02362±0.019685	0.01811±0.004724	≤0.49213	0.03543±0.00591
98036503	CLEAR	1-1/2"	1.61417±0.031496	0.019685±0.005118	≤0.82677	0.045275±0.00591



		HEAT SHRINK TUBING - 4 ft SINGLE WALL
AFTER AGING		
SHRINK TEMPERATURE	≥125°C	
SHRINK TIME	5 MINUTES	
TEMPERATURE RANGE	-40-125°C	
LONGITUDINAL SHRINKING RATIO	5~5%	
TENSILE STRENGTH	≥10.4 Mpa	
ELONGATION RATIO	≥200%	
AGING IN CIRCULATING-AIR OVEN	(158±1.0)°C, 7 DAYS	
TENSILE STRENGTH	≥7.3MPa	
ELONGATION RATIO	≥100%	
DIELECTRIC VOLTAGE WITHSTAND	600V	
VOLUME RESISTIVITY	≥1014Ω·CM	
VOLTAGE RESISTANCE	≥2500 (60s)	
CORROSION OF BARE COPPER	NO CORROSION	
HEAT SHOCK	NO CRACKING	
COLD BEND	NO CRACKING	
FLAMMABILITY	VW-1	
NOT TO SCALE		